



INDO TEX UV

Highly Elastomeric UV Resistant Acrylic Roof Protective Coating

DESCRIPTION

INDO TEX UV is a single component, highly elastomeric, acrylic waterproofing and protective coating with very good solar reflective property.

INDO TEX UV upon curing forms a tough, flexible and durable coating which is resistant to UV and other weathering agents.

INDO TEX UV is also used to protect exposed concrete structures against carbonation and chloride ion diffusion

TYPICAL USES

Used as waterproofing and protective coating for the following structures:

- Sloped concrete roofs, metal profile roofs & asbestos roofs
- Anti carbonation coating in car park decks
- Protective coating on underpasses & concrete bridge decks
- Protective coating on polyurethane foam insulation

ADVANTAGES

- Single Component, Easy to Apply
- Protects exposed concrete structures against Carbonation and ingress of atmospheric gases and salts
- Excellent UV resistance with very good solar reflective property
- Elastomeric -high crack bridging capability
- Excellent adhesion to most of the substrates

- Good resistance to dilute acids, alcohol, hydrocarbons, chloride and sulphate ions

TECHNICAL PROPERTIES

(The properties shown below were obtained under laboratory conditions).

Solid Content(by wt)	52 ± 2 %
Tensile strength, ASTM D 638	1 (N/mm ²)
Toxicity BS 6920	NON TOXIC
Hydrostatic pressure @5bar (50m) BSEN 12390 (part 8)	No Leakage
Elongation @break ASTM D 638	>300 %
UV Resistance @100 [hrs) ASTM G 154	Passes
Crack Bridging ability ASTM C 836	>9.5 mm
Application Temperature)	5 to 45 Degree C
Service temperature, [°C] -20 to 70	-20 TO 120deg.C

All values given are subject to 5-10% tolerance *
Values achieved with 800 microns thickness



APPLICATION INSTRUCTION

Application procedures may vary slightly depending upon site conditions. The general recommended guidelines for the application of the coating are as follows:

SURFACE PREPARATION

CONCRETE SURFACES

Clean the surfaces which shall receive the coating of all dust, dirt, moss, oil and grease, loose particles, cement laitance and all other deleterious materials which will affect the adhesion of the coating with the substrate. Cracks and potholes shall be repaired with concrete repair mortar from the SPADREP* range.

METAL SURFACES

Clean the surface of all rust scales. This can be achieved by wire brushing or grit blasting.

PRIMING

BAUCOAT WP PLUS shall be diluted with 20% water and applied as primer coat on the concrete surface to seal the pores and stabilize the surface.

The primer also functions as an adhesion promoter for the top coats. This primer coat can be applied by a brush, roller or airless spray and allowed to dry completely before the application of acrylic coating.

MIXING & APPLICATION

Mix the contents of the drum prior to the application to remove any sediment. INDO

TEX UV can be applied by soft bristled brush, roller or an airless spray.

When applying by airless spray then dilute the coating with approximately 5% water to reduce the viscosity of the coating.

Apply the first coat of undiluted material at a coverage rate of **1 lt. /2.5 m²/coat** to get a Dry Film thickness of 0.5 mm.

It is important to ensure that each coat has to be cured totally before applying the next coat. The second coat should be applied at right angle to the first at the same coverage rate, to ensure a full unbroken coating to the substrate.

For improved strength and flexibility, embed a 65 g/m² non woven geo-textile membrane whilst the first coat is still wet on all corner joints, fillets and pipe penetration joints.

Allow the coating to cure fully for 72 hours to achieve its full properties.

Caution: prolonged water stagnation will cause the coating to become soft and peel off. Adequate protective measures shall be taken when applying in water logging area

PACKAGING

INDO TEX UV is supplied in 20 Litres Pails and 200 Litres Drum.

COVERAGE

1 Ltr/ 2.5 m²/ coat for 0.5 mm Dry Film thickness. Two coats will give a combined thickness of 1.0mm approximately.



STORAGE

Store under cover, out of direct sunlight, clear of the ground on pallets and protect from extreme temperatures. In tropical

climate the product must be stored in air conditioned environment (<25°C).

Shelf life is 12 months when stored as above.

PRECAUTIONS

As with all construction chemicals products caution should always be exercised. Protective clothing such as gloves and goggles shall be worn.

Treat any splashes to the skin or eyes with fresh water immediately. Should any of the

products be accidentally swallowed, do not induce vomiting, but call for medical assistance immediately.

There are no known health hazards associated with INDO TEX UV.

Clean all the tools with water after use. Hardened materials can be removed mechanically only. Allow the waste to cure. Seal it into a suitable container and bury in landfill as per the local regulations.



P.O. Box: 231147, Dubai, U.A.E. T: +971 4 380 62 66 / 882 40 15 F: +971 4 882 36 09
W : www.indexemirates.com E: sales@indexemirates.com

Note: Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, as the conditions of any labor involved in the application is beyond our control. INDO TEX UV shall not be liable for any injury, loss or damage, direct or consequential, arising out of the use of this product. It is the responsibility of the user to ensure that the product meets his particular requirements and to use it in a suitable way. Field service, where provided, does not constitute supervisory responsibility. For additional Information contact your local INDO TEX UV representative.